

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C08K 3/04, C08L 67/06	A1	(11) International Publication Number: WO 00/49076 (43) International Publication Date: 24 August 2000 (24.08.00)
(21) International Application Number: PCT/US00/04262 (22) International Filing Date: 18 February 2000 (18.02.00) (30) Priority Data: 60/120,677 19 February 1999 (19.02.99) US (71) Applicant (for all designated States except US): UNION CARBIDE CHEMICALS & PLASTICS TECHNOLOGY CORPORATION [US/US]; 39-Old Ridgebury Road, Danbury, CT 06817-0001 (US). (71)(72) Applicant and Inventor: REX, Gary, Charles [US/US]; 5307 Stephen Way, Cross Lanes, WV 25313 (US). (74) Agent: PACCIONE, Stanley, Jesson; Union Carbide Chemicals & Plastics Technology Corporation, 39-Old Ridgebury Road, Danbury, CT 06817-0001 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ZA, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: CONDUCTIVE MOLDING COMPOSITIONS AND ARTICLES MOLDED THEREFROM (57) Abstract Electrically conductive, thermoset molding compositions are disclosed which comprise an unsaturated thermosetting resin, an olefinically unsaturated monomer which is copolymerizable with the thermosetting resin, a thermoplastic additive and carbon black. The carbon black is incorporated in a conductive additive which comprises the thermoplastic additive, the carbon black and, preferably, a lubricant. The electrical resistance of articles molded from the disclosed molding compositions is typically less than about 10 ⁸ ohms/cm ² .		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

CONDUCTIVE MOLDING COMPOSITIONS AND ARTICLES MOLDED THEREFROM

Field of the Invention

The present invention relates to conductive, thermoset molding compositions and articles made therefrom. More specifically, the present invention relates to molding compositions containing thermoplastic additives comprising conductive carbon black which can impart electrical conductivity to articles molded from the molding compositions.

Background of the Invention

Thermoset molding compositions are commonly used to make a variety of articles such as, for example, automotive body panels, truck cab components, appliances, home furnishings, e.g., bathtubs, doors, and the like. Such molding compositions typically comprise an unsaturated thermosetting resin, an olefinically unsaturated monomer which is copolymerizable with the thermosetting resin, a thermoplastic additive, fibrous materials, and various other ingredients, including for example, fillers, mold release agents, and the like.

In some cases, the molding compositions comprise a pigment which imparts a desired color to the molded article. In other cases, the molded articles are painted in order to provide the desired color. Electrostatic spray systems are being used more frequently in the industrial application of primers and paints because of improvements in the transfer efficiency, that is, the amount of primer or paint deposited on the article versus the amount of primer or paint sprayed.

-2-

In systems which do not utilize electrostatics spray processes, "bounce back" and "overspray" can reduce the transfer efficiency. Bounce back occurs as atomized droplets of paint approach the surface of the article and an air current rebounding from the same surface deflects the droplets into a new trajectory away from the article. Overspray occurs when a portion of the paint is sprayed beyond the article's edge into the surrounding space.

In electrostatic spray processes, atomized paint droplets are passed through an electric field charging the droplets. The droplets are drawn to the article to be painted which is at ground potential. If the article cannot conduct electric current, then the article becomes increasingly charged. This charge buildup on the articles' surface eventually repels new incoming charged droplets. This repulsion can lower the transfer efficiency quite dramatically. Therefore, it is highly desirable in electrostatic paint processes that the surface of the article be made conductive.

Both sheet molding compound ("SMC") and bulk molding compound ("BMC") are good insulators and have poor electrical conductivity. SMC and BMC molded articles can be made conductive by incorporating a conductive material, e.g., carbon black, into the molding composition or by applying a conductive coat (known in the art as a "dust coat") on the molded article. The incorporation of carbon black in its neat form into molding compositions is generally undesired in the art because handling carbon black presents significant housekeeping problems and health concerns. Applying a dust coat is

also generally undesirable because it adds an additional step to the painting process which often increases costs.

Accordingly, improved molding compositions are desired to provide electrically conductive molded articles which are suitable for electrostatic painting. Desirably, the improved molding compositions would allow molders of articles to avoid the necessity of handling neat carbon black and avoid the use of a dust coat in the electrostatic painting process.

Summary of the Invention

By the present invention, improved molding compositions suitable for manufacturing electrically conductive articles are provided. As a result, articles molded from the molding compositions of the present invention can be painted by electrostatic painting processes which can lead to enhancements in the transfer efficiency of the paint to the article, i.e, a reduction in bounce back and overspray and a corresponding reduction in the amount of volatile organic compounds released to the environment.

In accordance with the present invention, electrically conductive, carbon black is incorporated into compositions comprising a thermoplastic polymer (hereinafter referred to as "conductive additive"). The conductive additives are preferably prepared in the form of pellets or extrudate prior to their addition to the molding compositions. Quite advantageously, the incorporation of the conductive carbon black into the conductive additive avoids the necessity of handling carbon black in its neat form. Also, the amount

of carbon black introduced into the molding compositions can be more accurately controlled.

Quite surprisingly, it has been found in accordance with a preferred aspect of the present invention that by adding a lubricant, e.g., zinc stearate, during the manufacture of the conductive additives, the electrical conductivity of the conductive additive and the resulting molding composition in which it is incorporated, and articles molded therefrom, can be enhanced.

Detailed Description of the Invention

The carbon black suitable for use in accordance with the present invention can be any carbon black material which conducts electricity. Typically, the conductive carbon black will be in aggregate form, such aggregates having a particle size of from about 10 nanometers ("nm") to 75 nm, preferably about 15 to 40 nm, and more preferably about 20 to 30 nm. A typical aggregate of carbon black comprises a cluster, or bunch of particles ranging from about 1 micron (" μ m") to 10 μ m. Desirably the aggregates are touching or in close proximity to another aggregate in order for electrons to flow, known in the art as "tunnelling". Without being bound to any particular theory, this is believed to be fundamental to the mechanism of electrical conductivity. The surface area of the carbon black particles typically ranges from about 80 meters squared per gram (" m^2/g ") to 1400 m^2/g preferably from about 130 to 1300 m^2/g and more preferably from about 600 to 1,000 m^2/g .

The carbon black has a high pore volume if the aggregates comprise particles arranged in a highly branched structure. This is referred to in the art as a "high structure" and is very desirable for enhancing electrical conductivity. The degree of structure, low or high, is typically determined by the Di-butyl phthalate ("DBP") absorption value which has units of milliliters of DBP per 100 g carbon black ("ml/100 g carbon black"). Higher absorption of DBP means a higher structure. DBP absorption typically ranges from about 65 ml/100g to 500 ml/100g, preferably from about 120 ml/100g to 400 ml/100g and more preferably from about 140 ml/100g to 385 ml/100g.

Furthermore, the surface chemistry, or % volatility, is important if maximum conductivity is to be achieved. The "% volatility" refers to the oxygen containing functional groups present at the surface of the carbon black. A high concentration of these organic, functional groups may act as a barrier to the electron tunneling effect. If the electron tunneling is essential for efficient conductivity, the % volatility should be minimized. The % volatility of carbon black can typically range as high as 22% to as low as 0.4%. Generally, carbon black with a % volatility of less than about 1.0% is desired. Carbon black suitable for use in accordance with the present invention is available, for example, from Akzo Nobel Chemicals of Dobbs Ferry, NY, Cabot Corp. of Billerica, MA and Degussa Corp. of Rochelle Park, NJ. Further details concerning the selection of carbon black are known to those skilled in the art.

The thermoplastic additives suitable for use in accordance with the present invention can be any materials which have the desired

dimensional control effect, e.g., shrinkage control, on the molded article. Typical of such thermoplastic additives include for example, polystyrene, polyvinyl acetate homopolymers and copolymers, e.g., vinyl acetate copolymerized with acrylic acid, crotonic acid, vinyl chloride, polyurethanes, saturated straight-chain and cyclic polyesters, polyalkyl acrylates, or methacrylates and the like. Polyvinyl acetates and mixtures thereof with other thermoplastics are preferred thermoplastic additives for use in accordance with the present invention.

The weight average molecular weights of the thermoplastic additives of the present invention are from about 10,000 to 250,000, preferably from about 25,000 to 200,000 and more preferably from about 50,000 to 180,000 grams per gram mole ("g/g mole"). As used herein, the term "average molecular weight" means weight average molecular weight. Methods for determining weight average molecular weight are known to those skilled in the art. One preferred method for determining weight average molecular weight is gel permeation chromatography. The thermoplastic additives can be used in conjunction with lower molecular weight materials which can enhance their shrinkage control ability such as epoxys, lower reactivity secondary monomers and others. Examples of such approaches are disclosed in U.S. patents 4,525,498, 4,755,557, and 4,374,215.

One or more thermoplastic additives may be employed in the compositions of the present invention. Further details of the preferred thermoplastic additives suitable for use in accordance with the present invention are described, for example, in U.S. Patent No. 4,172,059.

Such thermoplastic additives are commercially available or alternatively can be prepared by those skilled in the art.

The lubricants suitable for use in the present invention can be any materials which are effective to enhance the electrical conductivity of the molded articles. Without being bound to any particular theory, it is believed that mechanical degradation of the carbon black aggregates can occur during the manufacture of the conductive additives, e.g., under the mixing shear and pressure that occurs, for example, during the melt extrusion of the thermoplastic additive with the carbon black. It is believed that such mechanical degradation can reduce the electrical conductivity of the conductive additives and hence, reduce the electrical conductivity of the articles molded from molding compositions comprising the conductive additives. Quite surprisingly in accordance with the present invention, it has been found that the incorporation of lubricants during the combination of the carbon black particles with the thermoplastic additive can enhance the electrical conductivity of the resulting conductive additives.

Preferably, the lubricants are selected from the group consisting of fatty acids and their metallic counterparts, for example, metallic stearates, polyalkylene glycols, polyalkylene oxides, detergents, phosphoric acid esters, polyether polyols, ethoxylated fatty acids, and mixtures thereof. Zinc stearate is an especially preferred lubricant for use in accordance with the present invention.

In making the conductive additives, the thermoplastic polymer or mixture of thermoplastic polymers is preferably combined, in a melted state, with the conductive carbon black and an effective amount

of the lubricant in order to enhance the electrical conductivity of the conductive additive.

The conductive additive typically comprises from about 5 to 40, more typically from about 5 to 39, most typically from about 5 to 30, preferably from about 10 to 25 and more preferably from about 15 to 20 weight percent carbon black, typically from about 60 to 95, more typically from about 60 to 94, preferably from about 67 to 88 and more preferably from about 75 to 85 weight percent of the thermoplastic additive, and typically from about 0 to 35, more typically from about 1 to 10 preferably from about 2 to 8 and more preferably from 4 to 6 weight percent of the lubricant, said percentages based on the total weight of the conductive additive.

The conductive additive can be made by any technique which is effective to combine the carbon black, thermoplastic additive and lubricant. Typical techniques include for example, mixing, rolling and melt mixing via extrusion, with extrusion being preferred. Suitable extruders include for example, twin screw extruders available from Berstorff Corp. of Charlotte, NC, Werner & Pfleiderer of Ramsey, NJ, or kneaders, available from Buss America of Bloomington, IL. Further details concerning suitable extruders are known to those skilled in the art. The temperature at which the combination of ingredients is conducted depends, for example, on the particular thermoplastic additive used. Typically, the temperature will range from about 100 to 200°C and preferably from about 130 to 160°C. The pressure under which the melt mixing is conducted is not critical.

Typical pressures range from about 100 to 2,000, preferably from about 300 to 1,000 psia.

Preferably, the shearing which occurs during melt mixing, e.g., extrusion, is reduced by the presence of the lubricant in accordance with the present invention. Preferably, the conductive carbon black aggregates will be substantially free of mechanical degradation after extrusion. A convenient method for melt mixing in the laboratory is the use of a Brabender torque rheometer available from Brabender Company, South Hackensack, New Jersey. It is also a convenient way to measure Peak Torque. As used herein, the term "Peak Torque" means the highest torque reading indicated after the carbon black has been added to the polymer, measured at 160°C and 60 revolutions per minute ("rpm") using a Brabender torque rheometer. It has been found in accordance with the present invention that the peak torque should be minimized during melt mixing and preferably should be less than about 1,000 Meter-gram ("M-g") and more preferably less than about 750 M-g.

The conductive additive may be prepared in any convenient form, e.g., as pellets, extrudate or spheres. Typically, the conductive additive is prepared as pellets having a size ranging from about 1.5 millimeters ("mm") to 4mm, and preferably from about 2mm to 3mm in diameter.

Further details on extrusion and other melt mixing techniques and effective conditions for making the conductive additives for use in accordance with the present invention are known to those skilled in the art.

-10-

The unsaturated thermosetting resins suitable for use in accordance with the present invention include those unsaturated polymeric materials which can be crosslinked to form thermoset articles. Typically, the unsaturated thermosetting resins have a weight average molecular weight of at least 500, preferably from about 500 to 10,000 g/g-mole.

Typical unsaturated thermosetting resins include, for example, epoxy diacrylates, polyester diacrylates, polyurethane diacrylates, acrylate capped polyurethane polyacrylates, acrylated polyacrylates, acrylated polyethers and the like. Especially preferred thermosetting resins include polyesters and vinyl esters. As used herein, the term "polyesters" also includes vinyl esters. Typically, the unsaturated thermosetting resins are; (i) a polyester resin comprising various combinations of anhydrides, such as maleic anhydride, and dicarboxylic acids, such as adipic acid or isophthalic acid, condensed with various diols such as propylene glycol, ethylene glycol, or 1,4-butanediol; or (ii) a vinyl ester resins comprising Novolac resins such as Derakane 780 or Bisphenol A based such as available from The Dow Chemical Company, Midland, MI Derakane 411-350. Such unsaturated thermosetting resins are commercially available or alternatively can be readily prepared by those skilled in the art. Examples of suitable unsaturated thermosetting resins for use in accordance with the present invention are described for example in U.S. Patent Nos. 4,172,059 and 4,942,001.

One or more unsaturated thermosetting resins may be employed in the molding compositions of the present invention. The total

amount of unsaturated thermosetting resins in the molding compositions of the present invention is typically from about 15 to 80 weight percent, preferably from about 20 to 60 weight percent, and more preferably from about 25 to 50 weight percent based on the weight of the unsaturated thermosetting resin, conductive additive and olefinically unsaturated monomer. Further details concerning the selection and amounts of unsaturated thermosetting resins are known to those skilled in the art.

The olefinically unsaturated monomers (also referred to herein as "crosslinking monomers") suitable for use in accordance with the present invention include materials which are copolymerizable with the unsaturated thermosetting resins. The monomer also serves the function of dissolving the thermosetting resin thereby by facilitating its interaction with the other components of the molding composition. Preferably, the olefinic unsaturation is due to ethylenic unsaturation. Typical olefinically unsaturated monomers include, for example, styrene, vinyl toluene isomers, methyl methacrylate, acryl nitrile and substituted styrene such as, for example, chlorostyrene and alphasubstituted styrene. Multifunctional monomers, such as, for example, divinylbenzene or multifunctional acrylates or methacrylates may also be employed. Styrene is a preferred monomer for use in the compositions of the present invention.

One or more olefinically unsaturated monomers may be used in the molding compositions of the present invention. Typically, the total amount of the olefinically unsaturated monomers is from about 1 to 80 weight percent, preferably from about 5 to 50 weight percent, and more

percent, based on the total weight of the molding composition and preferably 15 to 50 weight percent.

The molding compositions of the invention may also contain one or more other conventional additives, which are employed for their known purposes in the amounts known to those skilled in the art, e.g., about 0.5 to 10 weight percent based on the total weight of the molding composition. The following are illustrative of such additives:

1. Polymerization initiators such as t-butyl hydroperoxide, t-butyl perbenzoate, benzoyl peroxide, t-butyl peroctoate, cumene hydroperoxide, methyl ethyl ketone peroxide, peroxy ketals, and others known to the art, to catalyze the reaction between the olefinically unsaturated monomer and the thermosetting resin. The polymerization initiator is employed in a catalytically effective amount, such as from about 0.3 to about 3 weight percent, based on the weight of the unsaturated thermosetting resin, conductive additive and crosslinking monomer.

2. Fillers such as clay, alumina trihydrate, silica, calcium carbonate, and others known to the art;

3. Mold release agents or lubricants, such as zinc stearate, calcium stearate, and others known to the art;

4. Viscosity reducing additives;

5. Thickeners, such as magnesium oxide, magnesium hydroxide, calcium oxide, calcium hydroxide, zinc oxide, barium oxide and mixtures thereof; and

6. Water.

The molding compositions of the present invention can be prepared by methods known to those skilled in the art, such as for example, mixing the components in a suitable apparatus such as Hobart mixer at temperatures on the order of about 20 to 50°C. The components may be combined in any convenient order. Generally, it is preferable that the thermosetting resin and conductive additive are added in liquid form by preparing a solution thereof in the crosslinking monomer. All the liquid components are then typically mixed together before adding the fillers, thickening agents and optional ingredients.

Once formulated, the molding compositions can be molded into thermoset articles of the desired shape, e.g., automotive fenders, hoods, appliances, bathtubs, doors, and the like. The specific conditions used in the molding process depend on the composition being molded as well as upon the nature of the particular articles desired, the details of which are known to those skilled in the art. Typical molding pressures for use in accordance with the present invention are from about 30 to 2,000 psia, preferably from about 100 to 1500 psia, and more preferably from about 200 to 1000 psia. Suitable molding temperatures are from about 80 to 180°C, preferably from about 100 to 160°C and more preferably from about 120 to 150°C. Typical molding time periods range from about 0.5 to about 5 minutes or longer.

The molding compositions of the present invention are suitable for use, for example, as sheet molding compounds and bulk molding compounds. For example, sheet molding compound can be produced by laying down a first layer of the molding composition, i.e., paste, on a first layer of polyethylene film or the equivalent thereof, laying on this

first layer of the paste filler reinforcements such as chopped glass fibers, and laying thereover a second layer of the paste. The two layers of the paste with the filler reinforcements sandwiched therebetween are then topped with a second sheet of polyethylene film and the resulting composite (sheet molding compound) is stored. Bulk molding compound can be produced by the use of sigma blade mixers, plow blade mixers, kneaders and the like. Further details concerning the manufacture, handling and use of sheet molding compounds and bulk molding compounds are known to those skilled in the art.

The articles molded from the molding compositions of the present invention typically have an surface resistivity of less than about 10^8 , preferably less than about 10^7 and more preferably less than about 10^6 to 10^4 ohms per square centimeter (ohms/cm²). Molded sheets of the conductive additive preferably, have a surface resistivity of less than about 10 ohms/cm² and more preferably less than about 5 ohms/cm². Techniques for measuring surface resistivity are known to those skilled in the art, see, for example ASTM procedure D257. As a result, the articles molded from the molding compositions of the present invention are particularly suitable to be coated, e.g., painted, by electrostatic painting processes. In comparison, the surface resistivity of molded articles which do not comprise carbon black is typically greater than about 10^{12} ohms/cm². Details concerning electrostatic painting processes are known to those skilled in the art.

The following examples are provided for illustrative purposes and are not intended to limit the scope of the claims which follow.

DEFINITIONS

The following materials were used in the examples set forth below:

p-BQ - A five percent solution of parabenzoquinone in diallylphthalate.

Calcium Carbonate - A calcium carbonate filler having a particle size of 5 microns supplied by Georgia Marble of Kennesaw, Georgia and sold under the designation CalWhite II™.

PG 91148 - A mixture of magnesium and calcium hydroxides dispersed in a low molecular weight polyester available from Plasticolors, Inc. of Ashtabula, OH

Orthophthalic UPE - an unsaturated thermosetting resin (polyester) resin that is modified using typically 15-30 mole % orthophthalic acid substituted for maleic anhydride available from Ashland Chemical, Dublin, OH, as Q6710 (or MR 13031) and contains styrene monomer.

LPS - 4015 - A carboxylated poly(vinyl acetate), having a weight average molecular weight of about 75,000 to 100,000 g/mole available from Union Carbide Corp., Danbury CT.

zinc stearate -an internal mold release available from Synthetic products, Cleveland, OH.

VR-3 - a fatty acid viscosity reducer available from Union Carbide Corporation, Danbury, CT.

Conductive Carbon Black - A fine-particle form of microcrystalline carbon , available from Degussa Corp. of Rochelle Park, NJ.

-17-

tBIC - a peroxide initiator, t-Butyl-Isopropyl-Monoperoxy Carbonate, available from Atochem North America, Inc., Buffalo, NY.

DVB-CP - Chemically pure grade divinyl benzene available from Dow Chemical of Midland, MI.

Styrene - an olefinically unsaturated aromatic monomer available from Ashland Chemical of Dublin, OH.

Modifier E - an inhibitor solution consisting 5% solution of p-benzoquinone in Diallyl phthalate available from Ashland Chemical of Dublin, OH.

Ionol - Butylated hydroxy toluene inhibitor available from Eastman Chemical Company of Kingsport, TN.

Byk 995 - a proprietary viscosity reducer available from Byk Chemie of Canton, OH.

XVR-10 - a thickening control agent comprising a liquid fatty acid available from Union Carbide Corp., Danbury, CT.

General Procedure for Preparation of Bulk Molding Compound (BMC) Formulations

All the liquid components were weighed individually into a Hobart mixing pan placed on a Toledo balance. The pan was attached to a Model C-100 Hobart mixer (in a hood). The agitator was started at slow speed, then increased to medium speed to completely mix the liquids over a period of 3-4 minutes. The agitator was then stopped and the internal mold release agent and/or fatty acid was next added to the liquid from an ice cream carton. The Hobart mixer was restarted and the mold release agent mixed with the liquid until it was

-18-

completely wet out. The filler was next added to the pan contents (agitator off) then mixed, using medium to high speed, until a consistent paste was obtained. The mixer was again stopped and the weighed amount of thickening agent was mixed into the paste over a period of 2-3 minutes, the mixer was again stopped and ~ 175 grams of the paste were removed from the pan (using a large spatula) and transferred to a wide-mouthed 4 oz. Bottle. This paste sample was stored in the capped bottle at room temperature and the viscosity was measured periodically using a Model HBT 5X Brookfield Synchronic Lectric Viscometer on a Helipath Stand. Typical viscosities ranged from 10×10^6 to 80×10^6 centipoise ("cP").

After removal of the paste sample, the contents were reweighed and styrene loss made up, the chopped glass fibers were added slowly (from an ice cream carton) to the pan with the mixer running on slow speed. The mixer was run for ~ 30 seconds after all the glass was in the paste. This short time gave glass wet out without glass degradation. The pan was then removed from the mixer and separate portions of the BMC mix of ~ 450 grams each were removed using spatulas and transferred to aluminum foil lying on a balance pan (balance in the hood). The mix was tightly wrapped in the aluminum foil (to prevent loss of styrene via evaporation) and stored at room temperature until the viscosity of the retained paste sample reached molding viscosity. The weight of the BMC added to the foil varies with the molding application.

General Procedures for Preparation of Sheet Molding
Compound (SMC) Formulations

All the liquid components were weighed individually into a 5 gallon open top container placed on a Toledo balance. The contents of the container were the mixed (in a hood) with a high speed Cowles type dissolver. The agitator was started at a slow speed, then increased to medium speed to completely mix the liquids over a period of 2-3 minutes. The mold release agent and/or fatty acid was next added to the liquids from an ice cream carton and mixed until completely dispersed. The filler was next added gradually from a tared container until a consistent paste was obtained and the contents were then further mixed to a minimum temperature of 32°C. The thickener was next mixed into the paste over a period of 2-3 minutes, the mixer was stopped and ~ 175 grams of the paste was removed from the container and transferred to a wide-mouthed 4 oz. Bottle. The paste sample was stored in the capped bottle at room temperature and the viscosity measured periodically using a Model HBT 5X Brookfield Synchronic Viscometer on a Helipath Stand.

The balance of the paste was next added to the doctor boxed on the SMC machine where it was further combined with fiber glass (~ 1" fibers). The sheet molding compound (SMC) was then allowed to mature to molding viscosity and then molded into the desired article.

MOLDING FACILITIES
18" x 18" x 0.120" test panels

Flat panels were molded on a 75 TON Queens Hydraulic press. The press contained a matched dye set of 18" x 18" chrome plated molds. The female cavity was installed in the bottom and the male portion was at the top. Both molds were electrically heated and were controlled on separate circuits so that the molds could be operated at different temperatures. The top and bottom temperature was 148°C. The molding pressure which can be varied from 0-75 TON was run at 1000 psig. The cure time was 90 seconds and the closure speed was 12 inches/minute. The charge weight was 1200 grams. The molds did not contain ejector pins; therefore, the molded panel was removed with a rubber suction cup and the use of a stream of air. The panels were laid on a flat surface, weighted to keep them flat and allowed to cool overnight.

The electrical surface resistivity was measured with an Electro-tech Systems wide range resistance meter, model 872A that was equipped with a concentric electrical resistivity probe, model 803B. The measurements were performed in accordance with ASTM D 257. A surface resistivity measurement at 10 volts was made by placing the resistivity probe on the flat surface of a test panel. The decade switch of the resistance meter was adjusted to within the range of the analog meter. The surface resistivity, $\Omega/\text{sq.}$, (ohms per square centimeter), then was read directly. The reported surface resistivity values of Example 3 are an average of nine readings on each test panel.

Example 1Preparation of Conductive Additive

The Brabender Torque Rheometer is a machine able to simulate the hot melt mix conditions of a twin screw extruder and is capable of producing polymeric mixtures on a laboratory scale. Temperature, mix time, and rpm of the mixer can be varied as desired. The dependent variable, mixer torque, is indicated digitally and can be tracked via a strip chart recorder.

The LPS-4015 and zinc stearate were first weighed in the proper proportions to provide the compositions set forth in Table 1 and introduced into the Brabender mix chamber via a load funnel. The materials were mixed until the torque curve "lined out to insure a homogeneous dispersion. This torque value was recorded as the initial torque. The conductive carbon was added and the polymer peak temperature and the Peak Torque, the highest torque obtained, were recorded. The speed was adjusted after 5 minutes to 100 rpm. At a total mix time of 10 minutes, the mixing chamber was disassembled, the mixture was removed and allowed to cool. Table 1 displays the various compositions of the conductive additives.

-22-

Table 1 Brabender Hot Melt Mixing of Conductive Additives Mix Conditions Temperature - 160° C Initial RPM - 60 for 5 min. Final RPM - 100 for 5 min. Total Mix Time - 10 min.					
	Conductive Additives, wt. %				
Sample No.	1	2	3	4	5
LPS-4015	84	83	82	80	78
Conductive Carbon Black	16	16	16	16	16
Zinc Stearate	0	1	2	4	6

Example 2Preparation of Molding Compositions

Table 2 below shows the formulas used for examining the various compositions of conductive additives produced in Example 1.

Table 2 Formulations of Conductive Molding Compounds (weight part per 100 weight parts of Resin)						
Sample No.	6	7	8	9	10	11
Ortho Polyester Resin	60	60	60	60	60	60
Neulon Preblend T	4	4	4	4	4	4
DVB CP	3.9	3.9	3.9	3.9	3.9	3.9
styrene	29	29	29	29	29	29
Modifier E	0.5	0.5	0.5	0.5	0.5	0.5
Byk 995	3.3	3.3	3.3	3.3	3.3	3.3
Ionol (10% in styrene)	1	1	1	1	1	1
XVR-10	2	2	2	2	2	2

Table 2 (continued)

**Formulations of Conductive Molding Compounds (weight
part per 100 weight parts of Resin)**

Sample No.	6	7	8	9	10	11
Conductive Additive #1	16	---	---	---	---	---
Conductive Additive #2	---	16	---	---	---	---
Conductive Additive #3	---	---	16	---	---	---
Conductive Additive #4	---	---	---	16	---	---
Conductive Additive #5	---	---	---	---	16	---
LPS-4015	---	---	---	---	---	13.4
Conductive Carbon Black	---	---	---	---	---	2.6
All above components mixed until conductive additive was dissolved						
tBIC, phr	2.2	2.2	2.2	2.2	2.2	2.2
Zinc Stearate, phr	2	2	2	2	2	2
Calcium Carbonate, phr	180	180	180	180	180	180
PG 91148	16	16	16	16	16	16
1/2" chopped Fiberglass @ 15% by wt.						

All parameters were kept constant except the conductive additive.

Note that Sample 11 is the control where the conductive carbon was added directly to the resin formula and dispersed at that point. This conductive carbon was the same as in the conductive additives, but was not subjected to the high mix shear of the polymer melt and its degrading effects. Also, all components were pre-mixed until solids were dissolved/dispersed using a high shear Cowles blade. The polymerization initiator, tBIC, was added/mixed and then followed by

-24-

the addition of zinc stearate. The paste was transferred to the Hobart mixer where calcium carbonate was added and mixed at high speed. The thickener, PG-91148, was added/mixed under medium speed. Finally 15 wt.% of fiberglass was added, mixed and wetted out under low speed. The molding compound was then weighed out to the specified value, wrapped and allowed to mature for two days before molding.

Example 3

Electrical Resistance Measurements

Panels made in accordance with the compounding procedure described above were molded and tested for electrical conductivity. The results of the characterization are set forth in Table 3.

Example 3 gives Peak Torque recorded during the mixing of the conductive carbon into the polymer melt. Sample 6, which contains the conductive additive where no zinc stearate was used as a processing aid, had the highest Peak Torque and as expected the highest surface resistivity. As one progresses from Sample 7 through Sample 10, the level of the processing aid, zinc stearate, increases, the Peak Torque decreases, and the surface resistivity decreases as well. Sample 11 has no peak torque value because the conductive carbon black and the thermoplastic low profile additive were introduced directly into the molding formula. This is a best case condition that gave the least surface resistivity because the conductive carbon was not subjected to the mechanical degradation of the polymer melt

mixing process. Indeed, the surface resistivity was found to be 1×10^4 ohms.cm², the lowest recorded.

Table 3 Surface Resistivity versus Peak Torque						
Sample No.	6	7	8	9	10	11
Peak Torque, meter ² /gram	1250	950	748	698	680	---
Surface Resistivity, ohms/cm ²	4.0 x 10 ⁵	1.3 x 10 ⁵	1.3 x 10 ⁵	7.8 x 10 ⁴	6.3 x 10 ⁴	1 x 10 ⁴

Example 4

Electrostatic Painting of SMC Panels

SMC of a similar composition as the BMC panels described above were painted electrostatically in order to evaluate a conductive panel versus a non-conductive panel in the electrostatic and non-electrostatic painting processes.

In both processes an air assisted painting was used in the determination of transfer efficiency ("TE"). TE is defined as the percentage of solid coating material transferred to a substrate. TE can be determined if the values four major variables are known: line speed, target width, flow rate and total solids.

Line speed was determined by the movement of the application device (Nordson SCF AE-1) past the substrate. The spraymation moves the application device from left to right while valving open across the target. The movement of the device is a measure within the spraymation and electronically displayed in inches/minute.

-26-

Standardization is done manually by timing the movement of the spray device over a known distance, i.e. 24 inches, and manually calculated before each run.

Target Panel Width is merely the width of the SMC panel, 18 inches.

Flow Rate is the difference between two mass flow meters in a timed period to determine flow rate of the nozzles while the application device passed in front of the part. The UNICARB® system, available from Union Carbide Corporation, Danbury, CT, which is based on the use of super critical carbon dioxide (CO₂) as a solvent, was used in this experiment. To determine the CO₂ concentration a sample (Hoke) cylinder was used. The amount of total flow difference of the mass flow meters was then multiplied by the CO₂ concentration. This gave the volume of coating sprayed out of the application device during a timed interval. Mass flow is the calculated in /min. sprayed.

Total solids were determined by backing a 0.25g - 0.50g sample of the coating in aluminum sample pans for 60 minutes at 110°C.

The TE was calculated as below:

Line Speed seconds ("s")/foot ("ft") x Panel Width (ft) x Flow Rate (g/s) x Total Solids = Solids Sprayed (g)

The tare weight (g) of the target panel is determined. The panel is then coated, baked and then weighed (Solids + Tare weight (g)). The amount of solids applied to the panel is then determined.

Solids Applied (g) = (Solids + Tare weight (g)) - (Tare Weight (g))

TE (%) = (Solids Applied (g) / Solids Sprayed (g)) x 100

The first column of Table 4 shows the results of painting the panels electrostatically (ES). The TE of the conductive SMC panel is 44.4% versus that of the non-conductive SMC panel, 10.1%. The low TE of the non-conductive SMC panel appears to be the result of the charged paint droplets being repelled by the increasingly charged panel's surface, i.e., because the SMC is non-conductive a static charge cannot drain to ground fast enough to prevent charge accumulation. The next column is the non-ES painted panels and, as expected, the TE values are virtually the same for both types of SMC. However for the non-conductive, non-ES panel the TE is 33.3% or about 10% less than the conductive, ES painted panel.

Table 4 Transfer Efficiency Study of Painted SMC Panels		
	Electrostatic	Non- Electro- static (control)
Conductive	44.4%	33.3%
Non-Conductive	10.1%	34.4%

In addition to the specific aspects of the invention described above, those skilled in the art will recognize that other aspects are intended to be included within the scope of the claims which follow.

We Claim:

1. In a molding composition comprising:
 - (i) an unsaturated thermosetting resin;
 - (ii) an olefinically unsaturated monomer which is copolymerizable with the unsaturated thermosetting resin;
 - (iii) a thermoplastic additive; and
 - (iv) carbon black,the improvement wherein the composition further comprises an effective amount of a lubricant to enhance the electrical conductivity of an article molded from the molding composition.
2. The composition of claim 1 wherein the carbon black is in the form of aggregates having a particle size of from about 10 to 75 nanometers.
3. The composition of claim 2 wherein the carbon black aggregate comprise particles having a particle size of from about 1 to 10 microns.
4. The composition of claim 1 wherein the concentration of the carbon black particles is from about 0.1 to 10 wt % based on the weight of the unsaturated thermosetting resin, olefinically unsaturated monomer and thermoplastic additive.
5. The composition of claim 1 wherein the thermoplastic additive is a polyvinyl acetate homopolymer or copolymer having a weight average molecular weight of from about 50,000 to 180,000 grams per gram mole.
6. An article made from the molding composition of claim 1.

-29-

7. The article of claim 6 which has a surface resistivity of less than about 10^8 ohms/cm².

8. The article of claim 7 which has an surface resistivity of less than about 10^7 ohms/cm².

9. The article of claim 6 having a surface with a coating deposited thereon.

10. The article of 9 wherein the coating is applied by electrostatic painting.

11. An electrically conductive composition comprising:

- (a) from about 60 to 94 weight percent of a thermoplastic polymer having a weight average molecular weight of from about 10,000 to 250,000 grams per gram mole;
 - (b) from about 5 to 30 weight percent of carbon black;
- and

- (c) from about 1 to 10 weight percent of the lubricant:

said percentages based on the total weight of thermoplastic additive, carbon black and the lubricant.

12. The composition of claim 11 wherein the thermoplastic additive is a polyvinyl acetate homopolymer or copolymer having a weight average molecular weight of from about 50,000 to 180,000 grams per gram mole.

-30-

13. The composition of claim 11 comprising:
- (a) from about 67 to 88 weight percent of a thermoplastic polymer having a weight average molecular weight of from about 10,000 to 250,000 grams per gram mole;
 - (b) from about 10 to 25 weight percent of carbon black;
- and
- (c) from about 2 to 8 weight percent of the lubricant:
- said percentages based on the total weight of thermoplastic additive, carbon black and the lubricant.
14. The composition of claim 11 wherein the lubricant is selected from the group consisting of metal stearates, polyalkylene glycols, polyalkylene oxides, detergents, phosphoric acid esters, polyether polyols, and mixtures thereof.
15. The composition of claim 14 wherein the lubricant is zinc stearate.
16. The composition of claim 11 is in the form of extruded pellets.
17. A process for making an electrically conductive composition comprising combining a melted thermoplastic polymer having a weight average molecular weight of from about 10,000 to 250,000 grams per gram mole with carbon black and an effective

-31-

amount of a lubricant to enhance the electrical conductivity of the composition.

18. The process of claim 17 wherein the combining is conducted at a temperature of from about 100 to 200°C.

19. The process of claim 17 wherein the combining is conducted at a pressure of from about 100 to 2,000 psia.

20. The process of claim 17 wherein the combining is done under shearing conditions.

21. The process of claim 20 wherein the lubricant is effective to reduce the shear stress during the combining.

22. The process of claim 21 wherein the combining is conducted by extrusion.

23. The process of claim 22 wherein the Peak Torque of the composition is less than about 1000 M-g.

24. An electrically conductive composition comprising:

(a) from about 60 to 95 weight percent of a thermoplastic polymer having a weight average molecular weight of from about 10,000 to 250,000 grams per gram mole; and

-32-

(b) from about 5 to 40 weight percent of carbon black;

25. The composition of claim 24 wherein the thermoplastic additive is a polyvinyl acetate homopolymer or copolymer having a weight average molecular weight of from about 50,000 to 180,000 grams per gram mole.

26. The composition of claim 24 comprising:

(a) from about 67 to 88 weight percent of a thermoplastic polymer having a weight average molecular weight of from about 10,000 to 250,000 grams per gram mole; and

(b) from about 12 to 33 weight percent of carbon black.

27. The composition of claim 24 is in the form of extruded pellets.

28. A process for making an electrically conductive composition comprising combining a melted thermoplastic polymer having a weight average molecular weight of from about 10,000 to 250,000 grams per gram mole with carbon black.

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 00/04262

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 7 C08K3/04 C08L67/06

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08K C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 659 785 A (UNION CARBIDE CHEM PLASTIC) 28 June 1995 (1995-06-28) page 3, paragraph 2; table 2 ----	1,5,6, 11,12,15
P,X	EP 0 949 633 A (DSM NV) 13 October 1999 (1999-10-13) page 5 -page 6; examples ----	1,6,7, 11,14
X	DE 196 41 940 A (BASF AG) 16 April 1998 (1998-04-16) column 2, paragraph 2 column 3, paragraph 2 ----	1,6,15
A	EP 0 751 184 A (ATOHAAS HOLDING CV) 2 January 1997 (1997-01-02) claims 1,11,12,18; examples; table 6 page 2 -----	1,6,7,9, 10,12

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

*** Special categories of cited documents:**

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

Z document member of the same patent family

Date of the actual completion of the international search

23 May 2000

Date of mailing of the international search report

06/06/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Engel, S

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 00/04262

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0659785 A	28-06-1995	US 5401803 A DE 69412985 D DE 69412985 T	28-03-1995 08-10-1998 11-03-1999
EP 0949633 A	13-10-1999	EP 0947997 A	06-10-1999
DE 19641940 A	16-04-1998	NONE	
EP 0751184 A	02-01-1997	FR 2736058 A CA 2180282 A CN 1176973 A JP 9012903 A US 5869557 A	03-01-1997 31-12-1996 25-03-1998 14-01-1997 09-02-1999